

PVC RESIN DG-1000K

聚氯乙烯树脂 (GRADE DG-1000K)

ITEMS 项目	SPECIFICATIONS 规格	PACKING 包装
Average Polymerization degree Impurity particle, number/100g Volatile matter Bulk density g/ml 0.35mm Particle size Fish eyes number/100cm ² Initial whiteness Whiteness(160°C, 10min) VCM residuals ug/g K Value	1030+/-50 50 max 0.3% max 0.53+/-0.03 0.1% max 5 max 90% min 78% min 1 max 66-68	Packing in 25kg PP/kraft paper Packing in 550kg jumbo bag Packing in 1200kg jumbo bag
平均聚合度 杂质粒子数, 个/100g ≤ 挥发物 ≤ 表面密度 g/ml 0.35mm 筛余物 ≤ 鱼眼数 个/100 cm ² ≤ 原始白度 ≥ 白度(160°C, 10min) ≥ VCM 残留 ug/g ≤ K 值	1030+/-50 50 0.3% 0.53+/-0.03 0.1% 5 90% 78% 1 66-68	25 公斤复合牛皮纸袋 550 公斤吨袋 1200 公斤吨袋