

Product Description

EL-Lene H6670B is a high density polyethylene resin suitable for producing milk bottles by using Extrusion blow molding machine.

Typical Application

- Milk bottles
- Fruit juice bottles

Product Characteristics

- Good flowability, suitable for high speed blow molding machine
- Excellent stiffness
- Odorless
- Good printability
- Food contact applicable (Complies with U.S FDA 21 CFR 177.1520)

Physical Properties

Property	Test Method	Value	Unit
Melt Flow Rate	ASTM D 1238 @ 190°C, 2.16 kg	0.70	g/10 min
Density	ASTM D 1505	0.966	g/cm ³
Tensile Strength at Yield	ASTM D 638 @ Crosshead speed 50 mm/min	320	kg/cm ²
Tensile Strength at Break	ASTM D 638 @ Crosshead speed 50 mm/min	330	kg/cm ²
Elongation at Break	ASTM D 638 @ Crosshead speed 50 mm/min	1200	%
Flexural Modulus	ASTM D 790	15000	kg/cm ²
Notched Izod Impact	ASTM D 256 @ 23°C	15	kg.cm/cm
Hardness	ASTM D 2240	68	Shore D
ESCR	ASTM D 1693 @ 50°C (Condition B, Compression Molded, 25% Igepal)	24	hrs, F ₅₀
Melting Point	ASTM D 2117	132	°C
Vicat Softening Point	ASTM D 1525	128	°C
Brittleness Temperature	ASTM D 746	< - 60	°C

Note : Conversion factor for changing unit from kg/cm² to MPa is divided by 10.20

Processing Techniques

The actual extrusion condition depends on type of using machine, size and wall thickness of product required. Generally, melt temperature should be 170-180°C. 5-8 bar of blowing pressure is recommended.

Product Available Form

- Pellet

Product Handling

- 25 kg loose bag
- Big bag with specified weight

Product Technical Assistance

For technical assistance or further information on this product or any other EL-Lene products, please contact EL-Lene representatives.

The information presented in this data sheet is offered in good faith. SCG Plastics Co., Ltd. accepts no responsibility for the accuracy or interpretation of the information presented. The users have to establish for yourself the most suitable formulation, production method and control tests, to ensure the uniformity and quality of your product in compliance with all related laws.